



Filo per saldatura in acciaio inossidabile  
Fil pour souder en acier inoxydable  
Edestahl Draht

# WELDING WIRE STAINLESS STEEL

Product availability / Disponibilità prodotto  
Produit disponible / Verfügbare werkstoffe

Novametal	AWS A5.9	EN ISO 14343-A	W. Nr.
NMS 307	ER307*	18 8 Mn	1.4370
NMS 307SI	ER307*	18 8 Mn	1.4370
NMS 308AWS	ER308L, ER308	19 9 L	1.4316
NMS 308H	ER308H, ER308	19 9 H	1.4302
NMS 308LSI	ER308LSI, ER308SI	19 9 L Si	1.4316
NMS 308L-LF (low ferrite)	ER308L, ER308	19 9 L	1.4316
NMS 309H	ER309	22 12 H	1.4829*
NMS 309L	ER309L, ER309	22 12 L	1.4332
NMS 309LSI	ER309LSI, ER309SI	23 12 L Si	1.4332
NMS 1.4459	ER309LMo*, ER309Mo*	23 12 2 L	1.4459*
NMS 310	ER310	25 20	1.4842
NMS 312	ER312	25 9	1.4337
NMS 316AWS	ER316L, ER316	19 12 3 L	1.4430
NMS 316H	ER316H, ER316	19 12 3 H	1.4403*
NMS 316LSI	ER316LSI, ER316SI	19 12 3 L Si	1.4430
NMS 316L-LF (low ferrite)	ER316L, ER316	19 12 3 L	1.4430
NMS 1.4455	ER316LMn	20 16 3 Mn N L	1.4455*

Novametal	AWS A5.9	EN ISO 14343-A	W. Nr.
NMS 317L	ER317L, ER317	18 15 3 L	1.4438
NMS 318	ER318	19 12 3 Nb	1.4576
NMS 318SI	ER318*	19 12 3 Nb Si	1.4576
NMS 320LR	ER320LR, ER320	-	2.4660
NMS 347	ER347	19 9 Nb	1.4551
NMS 347-HF (high ferrite)	ER347	19 9 Nb	1.4551
NMS 347SI	ER347Si	19 9 Nb Si	1.4551
NMS 904L	ER385	20 25 5 Cu L	1.4519*
NMS 409	ER409Nb	409Nb* (EN ISO 14343-B)	1.4009*
NMS 410	ER410	13	1.4009*
NMS 1.4313	ER410NiMo	13 4	1.4313
NMS 420C	ER420	420 (EN ISO 14343-B)	1.4031
NMS 430	ER430	17	1.4015
NMS 430LNB	-	18 L Nb*	1.4511*
NMS 1.4502	ER439	439 (EN ISO 14343-B)	1.4502
NMS 630/S	ER630	630 (EN ISO 14343-B)	1.4542
NMS 1.4122	-	X39CrMo171 (EN 10088-1)	1.4122
NMS 1.4718	-	X 45 CrSi9-3 (EN 10090)	1.4718

\* = nearest equivalent